

YIELD CONVERSION TABLE : NUMBER 25

IWTO SCOURED YIELD, 16% REGAIN TO AUSTRALIAN CARBONISING YIELD

(WB = SCRD YIELD / 1.1869 - VM : ACY = WB * 1.1972 + VMB * 0.162 -5.12

AUSTRALIAN CARBONISING YIELD

SCRD	VEGETABLE MATTER BASE %												
	0.5	1.0	1.5	2.0	2.5	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0
35.0	29.7	29.1	28.6	28.1	27.6	27.1	26.0	25.0	24.0	22.9	21.9	20.9	19.8
36.0	30.7	30.2	29.6	29.1	28.6	28.1	27.1	26.0	25.0	23.9	22.9	21.9	20.8
37.0	31.7	31.2	30.6	30.1	29.6	29.1	28.1	27.0	26.0	25.0	23.9	22.9	21.8
38.0	32.7	32.2	31.7	31.1	30.6	30.1	29.1	28.0	27.0	26.0	24.9	23.9	22.9
39.0	33.7	33.2	32.7	32.1	31.6	31.1	30.1	29.0	28.0	27.0	25.9	24.9	23.9
40.0	34.7	34.2	33.7	33.2	32.6	32.1	31.1	30.1	29.0	28.0	26.9	25.9	24.9
41.0	35.7	35.2	34.7	34.2	33.6	33.1	32.1	31.1	30.0	29.0	28.0	26.9	25.9
42.0	36.7	36.2	35.7	35.2	34.7	34.1	33.1	32.1	31.0	30.0	29.0	27.9	26.9
43.0	37.7	37.2	36.7	36.2	35.7	35.1	34.1	33.1	32.0	31.0	30.0	28.9	27.9
44.0	38.7	38.2	37.7	37.2	36.7	36.2	35.1	34.1	33.1	32.0	31.0	29.9	28.9
45.0	39.8	39.2	38.7	38.2	37.7	37.2	36.1	35.1	34.1	33.0	32.0	31.0	29.9
46.0	40.8	40.2	39.7	39.2	38.7	38.2	37.1	36.1	35.1	34.0	33.0	32.0	30.9
47.0	41.8	41.3	40.7	40.2	39.7	39.2	38.1	37.1	36.1	35.0	34.0	33.0	31.9
48.0	42.8	42.3	41.7	41.2	40.7	40.2	39.2	38.1	37.1	36.1	35.0	34.0	32.9
49.0	43.8	43.3	42.8	42.2	41.7	41.2	40.2	39.1	38.1	37.1	36.0	35.0	34.0
50.0	44.8	44.3	43.8	43.2	42.7	42.2	41.2	40.1	39.1	38.1	37.0	36.0	35.0
51.0	45.8	45.3	44.8	44.3	43.7	43.2	42.2	41.1	40.1	39.1	38.0	37.0	36.0
52.0	46.8	46.3	45.8	45.3	44.7	44.2	43.2	42.2	41.1	40.1	39.0	38.0	37.0
53.0	47.8	47.3	46.8	46.3	45.8	45.2	44.2	43.2	42.1	41.1	40.1	39.0	38.0
54.0	48.8	48.3	47.8	47.3	46.8	46.2	45.2	44.2	43.1	42.1	41.1	40.0	39.0
55.0	49.8	49.3	48.8	48.3	47.8	47.3	46.2	45.2	44.1	43.1	42.1	41.0	40.0
56.0	50.8	50.3	49.8	49.3	48.8	48.3	47.2	46.2	45.2	44.1	43.1	42.0	41.0
57.0	51.9	51.3	50.8	50.3	49.8	49.3	48.2	47.2	46.2	45.1	44.1	43.1	42.0
58.0	52.9	52.3	51.8	51.3	50.8	50.3	49.2	48.2	47.2	46.1	45.1	44.1	43.0
59.0	53.9	53.4	52.8	52.3	51.8	51.3	50.3	49.2	48.2	47.1	46.1	45.1	44.0
60.0	54.9	54.4	53.8	53.3	52.8	52.3	51.3	50.2	49.2	48.2	47.1	46.1	45.0
61.0	55.9	55.4	54.9	54.3	53.8	53.3	52.3	51.2	50.2	49.2	48.1	47.1	46.1
62.0	56.9	56.4	55.9	55.3	54.8	54.3	53.3	52.2	51.2	50.2	49.1	48.1	47.1
63.0	57.9	57.4	56.9	56.4	55.8	55.3	54.3	53.3	52.2	51.2	50.1	49.1	48.1
64.0	58.9	58.4	57.9	57.4	56.8	56.3	55.3	54.3	53.2	52.2	51.2	50.1	49.1
65.0	59.9	59.4	58.9	58.4	57.9	57.3	56.3	55.3	54.2	53.2	52.2	51.1	50.1
66.0	60.9	60.4	59.9	59.4	58.9	58.3	57.3	56.3	55.2	54.2	53.2	52.1	51.1
67.0	61.9	61.4	60.9	60.4	59.9	59.4	58.3	57.3	56.3	55.2	54.2	53.1	52.1
68.0	63.0	62.4	61.9	61.4	60.9	60.4	59.3	58.3	57.3	56.2	55.2	54.2	53.1
69.0	64.0	63.4	62.9	62.4	61.9	61.4	60.3	59.3	58.3	57.2	56.2	55.2	54.1
70.0	65.0	64.5	63.9	63.4	62.9	62.4	61.3	60.3	59.3	58.2	57.2	56.2	55.1
71.0	66.0	65.5	64.9	64.4	63.9	63.4	62.4	61.3	60.3	59.2	58.2	57.2	56.1
72.0	67.0	66.5	66.0	65.4	64.9	64.4	63.4	62.3	61.3	60.3	59.2	58.2	57.2
73.0	68.0	67.5	67.0	66.4	65.9	65.4	64.4	63.3	62.3	61.3	60.2	59.2	58.2
74.0	69.0	68.5	68.0	67.5	66.9	66.4	65.4	64.3	63.3	62.3	61.2	60.2	59.2
75.0	70.0	69.5	69.0	68.5	67.9	67.4	66.4	65.4	64.3	63.3	62.2	61.2	60.2
76.0	71.0	70.5	70.0	69.5	69.0	68.4	67.4	66.4	65.3	64.3	63.3	62.2	61.2
77.0	72.0	71.5	71.0	70.5	70.0	69.4	68.4	67.4	66.3	65.3	64.3	63.2	62.2
78.0	73.0	72.5	72.0	71.5	71.0	70.5	69.4	68.4	67.3	66.3	65.3	64.2	63.2
79.0	74.0	73.5	73.0	72.5	72.0	71.5	70.4	69.4	68.4	67.3	66.3	65.2	64.2
80.0	75.1	74.5	74.0	73.5	73.0	72.5	71.4	70.4	69.4	68.3	67.3	66.3	65.2

YIELD CONVERSION TABLE : NUMBER 26

IWTO SCOURED YIELD, 16% REGAIN TO JAPANESE CLEAN SCOURED YIELD

(WB = SCRD YIELD / 1.1869 - VM : JCSY = WB * 1.1777)

JAPANESE CLEAN SCOURED YIELD

SCRD	VEGETABLE MATTER BASE %												
	0.5	1.0	1.5	2.0	2.5	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0
35.0	34.1	33.6	33.0	32.4	31.8	31.2	30.0	28.8	27.7	26.5	25.3	24.1	23.0
36.0	35.1	34.5	34.0	33.4	32.8	32.2	31.0	29.8	28.7	27.5	26.3	25.1	23.9
37.0	36.1	35.5	34.9	34.4	33.8	33.2	32.0	30.8	29.6	28.5	27.3	26.1	24.9
38.0	37.1	36.5	35.9	35.4	34.8	34.2	33.0	31.8	30.6	29.5	28.3	27.1	25.9
39.0	38.1	37.5	36.9	36.3	35.8	35.2	34.0	32.8	31.6	30.5	29.3	28.1	26.9
40.0	39.1	38.5	37.9	37.3	36.7	36.2	35.0	33.8	32.6	31.4	30.3	29.1	27.9
41.0	40.1	39.5	38.9	38.3	37.7	37.1	36.0	34.8	33.6	32.4	31.3	30.1	28.9
42.0	41.1	40.5	39.9	39.3	38.7	38.1	37.0	35.8	34.6	33.4	32.3	31.1	29.9
43.0	42.1	41.5	40.9	40.3	39.7	39.1	38.0	36.8	35.6	34.4	33.2	32.1	30.9
44.0	43.1	42.5	41.9	41.3	40.7	40.1	38.9	37.8	36.6	35.4	34.2	33.1	31.9
45.0	44.1	43.5	42.9	42.3	41.7	41.1	39.9	38.8	37.6	36.4	35.2	34.1	32.9
46.0	45.1	44.5	43.9	43.3	42.7	42.1	40.9	39.8	38.6	37.4	36.2	35.0	33.9
47.0	46.0	45.5	44.9	44.3	43.7	43.1	41.9	40.7	39.6	38.4	37.2	36.0	34.9
48.0	47.0	46.5	45.9	45.3	44.7	44.1	42.9	41.7	40.6	39.4	38.2	37.0	35.9
49.0	48.0	47.4	46.9	46.3	45.7	45.1	43.9	42.7	41.6	40.4	39.2	38.0	36.8
50.0	49.0	48.4	47.8	47.3	46.7	46.1	44.9	43.7	42.5	41.4	40.2	39.0	37.8
51.0	50.0	49.4	48.8	48.2	47.7	47.1	45.9	44.7	43.5	42.4	41.2	40.0	38.8
52.0	51.0	50.4	49.8	49.2	48.7	48.1	46.9	45.7	44.5	43.4	42.2	41.0	39.8
53.0	52.0	51.4	50.8	50.2	49.6	49.1	47.9	46.7	45.5	44.3	43.2	42.0	40.8
54.0	53.0	52.4	51.8	51.2	50.6	50.0	48.9	47.7	46.5	45.3	44.2	43.0	41.8
55.0	54.0	53.4	52.8	52.2	51.6	51.0	49.9	48.7	47.5	46.3	45.2	44.0	42.8
56.0	55.0	54.4	53.8	53.2	52.6	52.0	50.9	49.7	48.5	47.3	46.1	45.0	43.8
57.0	56.0	55.4	54.8	54.2	53.6	53.0	51.8	50.7	49.5	48.3	47.1	46.0	44.8
58.0	57.0	56.4	55.8	55.2	54.6	54.0	52.8	51.7	50.5	49.3	48.1	47.0	45.8
59.0	58.0	57.4	56.8	56.2	55.6	55.0	53.8	52.7	51.5	50.3	49.1	47.9	46.8
60.0	58.9	58.4	57.8	57.2	56.6	56.0	54.8	53.6	52.5	51.3	50.1	48.9	47.8
61.0	59.9	59.3	58.8	58.2	57.6	57.0	55.8	54.6	53.5	52.3	51.1	49.9	48.8
62.0	60.9	60.3	59.8	59.2	58.6	58.0	56.8	55.6	54.5	53.3	52.1	50.9	49.7
63.0	61.9	61.3	60.7	60.2	59.6	59.0	57.8	56.6	55.4	54.3	53.1	51.9	50.7
64.0	62.9	62.3	61.7	61.1	60.6	60.0	58.8	57.6	56.4	55.3	54.1	52.9	51.7
65.0	63.9	63.3	62.7	62.1	61.6	61.0	59.8	58.6	57.4	56.3	55.1	53.9	52.7
66.0	64.9	64.3	63.7	63.1	62.5	62.0	60.8	59.6	58.4	57.2	56.1	54.9	53.7
67.0	65.9	65.3	64.7	64.1	63.5	62.9	61.8	60.6	59.4	58.2	57.1	55.9	54.7
68.0	66.9	66.3	65.7	65.1	64.5	63.9	62.8	61.6	60.4	59.2	58.1	56.9	55.7
69.0	67.9	67.3	66.7	66.1	65.5	64.9	63.8	62.6	61.4	60.2	59.0	57.9	56.7
70.0	68.9	68.3	67.7	67.1	66.5	65.9	64.7	63.6	62.4	61.2	60.0	58.9	57.7
71.0	69.9	69.3	68.7	68.1	67.5	66.9	65.7	64.6	63.4	62.2	61.0	59.9	58.7
72.0	70.9	70.3	69.7	69.1	68.5	67.9	66.7	65.6	64.4	63.2	62.0	60.8	59.7
73.0	71.8	71.3	70.7	70.1	69.5	68.9	67.7	66.5	65.4	64.2	63.0	61.8	60.7
74.0	72.8	72.2	71.7	71.1	70.5	69.9	68.7	67.5	66.4	65.2	64.0	62.8	61.6
75.0	73.8	73.2	72.7	72.1	71.5	70.9	69.7	68.5	67.4	66.2	65.0	63.8	62.6
76.0	74.8	74.2	73.6	73.1	72.5	71.9	70.7	69.5	68.3	67.2	66.0	64.8	63.6
77.0	75.8	75.2	74.6	74.0	73.5	72.9	71.7	70.5	69.3	68.2	67.0	65.8	64.6
78.0	76.8	76.2	75.6	75.0	74.5	73.9	72.7	71.5	70.3	69.2	68.0	66.8	65.6
79.0	77.8	77.2	76.6	76.0	75.4	74.9	73.7	72.5	71.3	70.1	69.0	67.8	66.6
80.0	78.8	78.2	77.6	77.0	76.4	75.8	74.7	73.5	72.3	71.1	70.0	68.8	67.6

YIELD CONVERSION TABLE : NUMBER 27

IWTO SCOURED YIELD, 16% REGAIN TO SCHLUMBERGER DRY T&N YIELD (1.0% TFM)
 (WB = SCRD YIELD / 1.1869 - VM : SCLUM DRY = WB * 1.207 - [7.7- (40.6 / (7.8+ VMB - HH))]
 SCLUMBERGER DRY T&N YIELD (1.0% TFM)

SCRD	VEGETABLE MATTER BASE %												
	0.5	1.0	1.5	2.0	2.5	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0
35.0	32.2	31.3	30.4	29.6	28.8	28.0	26.5	25.0	23.6	22.2	20.8	19.4	18.1
36.0	33.2	32.3	31.5	30.6	29.8	29.0	27.5	26.0	24.6	23.2	21.8	20.5	19.1
37.0	34.2	33.3	32.5	31.7	30.9	30.1	28.5	27.1	25.6	24.2	22.8	21.5	20.1
38.0	35.2	34.4	33.5	32.7	31.9	31.1	29.6	28.1	26.6	25.2	23.9	22.5	21.2
39.0	36.2	35.4	34.5	33.7	32.9	32.1	30.6	29.1	27.7	26.3	24.9	23.5	22.2
40.0	37.3	36.4	35.5	34.7	33.9	33.1	31.6	30.1	28.7	27.3	25.9	24.5	23.2
41.0	38.3	37.4	36.5	35.7	34.9	34.1	32.6	31.1	29.7	28.3	26.9	25.5	24.2
42.0	39.3	38.4	37.6	36.7	35.9	35.1	33.6	32.1	30.7	29.3	27.9	26.6	25.2
43.0	40.3	39.4	38.6	37.8	37.0	36.2	34.6	33.2	31.7	30.3	28.9	27.6	26.2
44.0	41.3	40.5	39.6	38.8	38.0	37.2	35.7	34.2	32.7	31.3	30.0	28.6	27.3
45.0	42.4	41.5	40.6	39.8	39.0	38.2	36.7	35.2	33.8	32.4	31.0	29.6	28.3
46.0	43.4	42.5	41.6	40.8	40.0	39.2	37.7	36.2	34.8	33.4	32.0	30.6	29.3
47.0	44.4	43.5	42.7	41.8	41.0	40.2	38.7	37.2	35.8	34.4	33.0	31.6	30.3
48.0	45.4	44.5	43.7	42.8	42.0	41.3	39.7	38.2	36.8	35.4	34.0	32.7	31.3
49.0	46.4	45.5	44.7	43.9	43.1	42.3	40.7	39.3	37.8	36.4	35.0	33.7	32.3
50.0	47.4	46.6	45.7	44.9	44.1	43.3	41.8	40.3	38.8	37.4	36.1	34.7	33.4
51.0	48.5	47.6	46.7	45.9	45.1	44.3	42.8	41.3	39.9	38.5	37.1	35.7	34.4
52.0	49.5	48.6	47.7	46.9	46.1	45.3	43.8	42.3	40.9	39.5	38.1	36.7	35.4
53.0	50.5	49.6	48.8	47.9	47.1	46.3	44.8	43.3	41.9	40.5	39.1	37.8	36.4
54.0	51.5	50.6	49.8	48.9	48.1	47.4	45.8	44.4	42.9	41.5	40.1	38.8	37.4
55.0	52.5	51.6	50.8	50.0	49.2	48.4	46.8	45.4	43.9	42.5	41.1	39.8	38.4
56.0	53.5	52.7	51.8	51.0	50.2	49.4	47.9	46.4	44.9	43.5	42.2	40.8	39.5
57.0	54.6	53.7	52.8	52.0	51.2	50.4	48.9	47.4	46.0	44.6	43.2	41.8	40.5
58.0	55.6	54.7	53.8	53.0	52.2	51.4	49.9	48.4	47.0	45.6	44.2	42.8	41.5
59.0	56.6	55.7	54.9	54.0	53.2	52.4	50.9	49.4	48.0	46.6	45.2	43.9	42.5
60.0	57.6	56.7	55.9	55.0	54.2	53.5	51.9	50.5	49.0	47.6	46.2	44.9	43.5
61.0	58.6	57.7	56.9	56.1	55.3	54.5	52.9	51.5	50.0	48.6	47.2	45.9	44.5
62.0	59.6	58.8	57.9	57.1	56.3	55.5	54.0	52.5	51.0	49.6	48.3	46.9	45.6
63.0	60.7	59.8	58.9	58.1	57.3	56.5	55.0	53.5	52.1	50.7	49.3	47.9	46.6
64.0	61.7	60.8	59.9	59.1	58.3	57.5	56.0	54.5	53.1	51.7	50.3	48.9	47.6
65.0	62.7	61.8	61.0	60.1	59.3	58.5	57.0	55.5	54.1	52.7	51.3	50.0	48.6
66.0	63.7	62.8	62.0	61.1	60.3	59.6	58.0	56.6	55.1	53.7	52.3	51.0	49.6
67.0	64.7	63.8	63.0	62.2	61.4	60.6	59.0	57.6	56.1	54.7	53.3	52.0	50.6
68.0	65.7	64.9	64.0	63.2	62.4	61.6	60.1	58.6	57.2	55.7	54.4	53.0	51.7
69.0	66.8	65.9	65.0	64.2	63.4	62.6	61.1	59.6	58.2	56.8	55.4	54.0	52.7
70.0	67.8	66.9	66.0	65.2	64.4	63.6	62.1	60.6	59.2	57.8	56.4	55.0	53.7
71.0	68.8	67.9	67.1	66.2	65.4	64.6	63.1	61.6	60.2	58.8	57.4	56.1	54.7
72.0	69.8	68.9	68.1	67.2	66.4	65.7	64.1	62.7	61.2	59.8	58.4	57.1	55.7
73.0	70.8	69.9	69.1	68.3	67.5	66.7	65.1	63.7	62.2	60.8	59.4	58.1	56.7
74.0	71.8	71.0	70.1	69.3	68.5	67.7	66.2	64.7	63.3	61.8	60.5	59.1	57.8
75.0	72.9	72.0	71.1	70.3	69.5	68.7	67.2	65.7	64.3	62.9	61.5	60.1	58.8
76.0	73.9	73.0	72.1	71.3	70.5	69.7	68.2	66.7	65.3	63.9	62.5	61.1	59.8
77.0	74.9	74.0	73.2	72.3	71.5	70.7	69.2	67.7	66.3	64.9	63.5	62.2	60.8
78.0	75.9	75.0	74.2	73.3	72.5	71.8	70.2	68.8	67.3	65.9	64.5	63.2	61.8
79.0	76.9	76.0	75.2	74.4	73.6	72.8	71.3	69.8	68.3	66.9	65.6	64.2	62.8
80.0	77.9	77.1	76.2	75.4	74.6	73.8	72.3	70.8	69.4	67.9	66.6	65.2	63.9

IWTO SCOURED YIELD, 16% REGAIN TO IWTO SCOURED YIELD, 17% REGAIN
 (WB = SCRD YIELD 16% / 1.1869 - VM : SCRD YIELD 17% = (WB + VMB) * 1.1972)
 IWTO SCOURED YIELD, 17% REGAIN

[illegible]

YIELD CONVERSION TABLE : NUMBER 29

IWTO SCOURED YIELD, 16% REGAIN TO ASTM CLEAN WOOL FIBRES PRESENT

(WB = SCRD YIELD / 1.1869 - VM : ASTM CWFP = WB / 0.86)

ASTM CLEAN WOOL FIBRES PRESENT

SCRD	VEGETABLE MATTER BASE %												
	0.5	1.0	1.5	2.0	2.5	3.0	4.0	5.0	6.0	7.0	8.0	9.0	10.0
35.0	33.7	33.1	32.5	32.0	31.4	30.8	29.6	28.5	27.3	26.1	25.0	23.8	22.7
36.0	34.7	34.1	33.5	32.9	32.4	31.8	30.6	29.5	28.3	27.1	26.0	24.8	23.6
37.0	35.7	35.1	34.5	33.9	33.3	32.8	31.6	30.4	29.3	28.1	26.9	25.8	24.6
38.0	36.6	36.1	35.5	34.9	34.3	33.7	32.6	31.4	30.3	29.1	27.9	26.8	25.6
39.0	37.6	37.0	36.5	35.9	35.3	34.7	33.6	32.4	31.2	30.1	28.9	27.7	26.6
40.0	38.6	38.0	37.4	36.9	36.3	35.7	34.5	33.4	32.2	31.0	29.9	28.7	27.6
41.0	39.6	39.0	38.4	37.8	37.3	36.7	35.5	34.4	33.2	32.0	30.9	29.7	28.5
42.0	40.6	40.0	39.4	38.8	38.2	37.7	36.5	35.3	34.2	33.0	31.8	30.7	29.5
43.0	41.5	41.0	40.4	39.8	39.2	38.6	37.5	36.3	35.1	34.0	32.8	31.7	30.5
44.0	42.5	41.9	41.4	40.8	40.2	39.6	38.5	37.3	36.1	35.0	33.8	32.6	31.5
45.0	43.5	42.9	42.3	41.8	41.2	40.6	39.4	38.3	37.1	35.9	34.8	33.6	32.5
46.0	44.5	43.9	43.3	42.7	42.2	41.6	40.4	39.3	38.1	36.9	35.8	34.6	33.4
47.0	45.5	44.9	44.3	43.7	43.1	42.6	41.4	40.2	39.1	37.9	36.7	35.6	34.4
48.0	46.4	45.9	45.3	44.7	44.1	43.5	42.4	41.2	40.0	38.9	37.7	36.6	35.4
49.0	47.4	46.8	46.3	45.7	45.1	44.5	43.4	42.2	41.0	39.9	38.7	37.5	36.4
50.0	48.4	47.8	47.2	46.7	46.1	45.5	44.3	43.2	42.0	40.8	39.7	38.5	37.4
51.0	49.4	48.8	48.2	47.6	47.1	46.5	45.3	44.2	43.0	41.8	40.7	39.5	38.3
52.0	50.4	49.8	49.2	48.6	48.0	47.5	46.3	45.1	44.0	42.8	41.6	40.5	39.3
53.0	51.3	50.8	50.2	49.6	49.0	48.4	47.3	46.1	44.9	43.8	42.6	41.5	40.3
54.0	52.3	51.7	51.2	50.6	50.0	49.4	48.3	47.1	45.9	44.8	43.6	42.4	41.3
55.0	53.3	52.7	52.1	51.6	51.0	50.4	49.2	48.1	46.9	45.7	44.6	43.4	42.3
56.0	54.3	53.7	53.1	52.5	52.0	51.4	50.2	49.0	47.9	46.7	45.6	44.4	43.2
57.0	55.3	54.7	54.1	53.5	52.9	52.4	51.2	50.0	48.9	47.7	46.5	45.4	44.2
58.0	56.2	55.7	55.1	54.5	53.9	53.3	52.2	51.0	49.8	48.7	47.5	46.4	45.2
59.0	57.2	56.6	56.1	55.5	54.9	54.3	53.2	52.0	50.8	49.7	48.5	47.3	46.2
60.0	58.2	57.6	57.0	56.5	55.9	55.3	54.1	53.0	51.8	50.6	49.5	48.3	47.2
61.0	59.2	58.6	58.0	57.4	56.9	56.3	55.1	53.9	52.8	51.6	50.5	49.3	48.1
62.0	60.2	59.6	59.0	58.4	57.8	57.3	56.1	54.9	53.8	52.6	51.4	50.3	49.1
63.0	61.1	60.6	60.0	59.4	58.8	58.2	57.1	55.9	54.7	53.6	52.4	51.3	50.1
64.0	62.1	61.5	61.0	60.4	59.8	59.2	58.0	56.9	55.7	54.6	53.4	52.2	51.1
65.0	63.1	62.5	61.9	61.4	60.8	60.2	59.0	57.9	56.7	55.5	54.4	53.2	52.1
66.0	64.1	63.5	62.9	62.3	61.8	61.2	60.0	58.8	57.7	56.5	55.4	54.2	53.0
67.0	65.1	64.5	63.9	63.3	62.7	62.2	61.0	59.8	58.7	57.5	56.3	55.2	54.0
68.0	66.0	65.5	64.9	64.3	63.7	63.1	62.0	60.8	59.6	58.5	57.3	56.2	55.0
69.0	67.0	66.4	65.9	65.3	64.7	64.1	62.9	61.8	60.6	59.5	58.3	57.1	56.0
70.0	68.0	67.4	66.8	66.3	65.7	65.1	63.9	62.8	61.6	60.4	59.3	58.1	57.0
71.0	69.0	68.4	67.8	67.2	66.7	66.1	64.9	63.7	62.6	61.4	60.3	59.1	57.9
72.0	70.0	69.4	68.8	68.2	67.6	67.0	65.9	64.7	63.6	62.4	61.2	60.1	58.9
73.0	70.9	70.4	69.8	69.2	68.6	68.0	66.9	65.7	64.5	63.4	62.2	61.1	59.9
74.0	71.9	71.3	70.8	70.2	69.6	69.0	67.8	66.7	65.5	64.4	63.2	62.0	60.9
75.0	72.9	72.3	71.7	71.2	70.6	70.0	68.8	67.7	66.5	65.3	64.2	63.0	61.8
76.0	73.9	73.3	72.7	72.1	71.5	71.0	69.8	68.6	67.5	66.3	65.2	64.0	62.8
77.0	74.9	74.3	73.7	73.1	72.5	71.9	70.8	69.6	68.5	67.3	66.1	65.0	63.8
78.0	75.8	75.3	74.7	74.1	73.5	72.9	71.8	70.6	69.4	68.3	67.1	66.0	64.8
79.0	76.8	76.2	75.7	75.1	74.5	73.9	72.7	71.6	70.4	69.3	68.1	66.9	65.8
80.0	77.8	77.2	76.6	76.0	75.5	74.9	73.7	72.6	71.4	70.2	69.1	67.9	66.7

IWTO SCOURD YIELD, 16% REGAIN TO ASTM LAB SCOURD YIELD, 13.64% REGAIN
 (WB = SCRD YIELD / 1.1869 - VM : ASTM LAB SCRD YLD = (WB + VMB) / 0.86)
 ASTM LAB SCOURD YIELD, 13.64% REGAIN

[illegible]